



Patent  
Attorney's Docket No. 024444-819



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

UTILITY PATENT  
APPLICATION TRANSMITTAL LETTER

Box PATENT APPLICATION

Assistant Commissioner for Patents  
Washington, D.C. 20231

Sir:

Enclosed for filing is the utility patent application of Åke ÖSTLUND, Jeanette PERSSON and Rickard SUNDSTRÖM for COATED MILLING INSERT.

Also enclosed are:

- ☐ \_\_\_\_\_ sheet(s) of ☐ formal ☐ informal drawing(s);
- ☒ a claim for foreign priority under 35 U.S.C. §§ 119 and/or 365 is ☒ hereby made to 9903090-0 filed in Sweden on September 1, 1999; ☒ in the declaration;
- ☐ a certified copy of the priority document;
- ☐ a General Authorization for Petitions for Extensions of Time and Payment of Fees;
- ☐ \_\_\_\_\_ statement(s) claiming small entity status;
- ☐ an Assignment document;
- ☐ an Information Disclosure Statement; and
- ☐ Other: \_\_\_\_\_
- ☒ An ☐ executed ☒ unexecuted declaration of the inventor(s) ☒ also is enclosed ☐ will follow.
- ☐ Please amend the specification by inserting before the first line the sentence --This application claims priority under 35 U.S.C. §§119 and/or 365 to \_ filed in \_ on \_; the entire content of which is hereby incorporated by reference.--
- ☐ A bibliographic data entry sheet is enclosed.



21839

[X] The filing fee has been calculated as follows [ ] and in accordance with the enclosed preliminary amendment:

C L A I M S					
	NO. OF CLAIMS		EXTRA CLAIMS	RATE	FEE
Basic Application Fee					\$690.00 (101)
Total Claims	10	MINUS 20 =	0	x \$18.00 (103)	--
Independent Claims	2	MINUS 3 =	0	x \$78.00 (102)	--
If multiple dependent claims are presented, add \$260.00 (104)					
Total Application Fee					\$690.00
If verified Statement claiming small entity status is enclosed, subtract 50% of Total Application Fee					
Add Assignment Recording Fee if Assignment document is enclosed					
<b>TOTAL APPLICATION FEE DUE</b>					<b>\$690.00</b>

[ ] This application is being filed without a filing fee. Issuance of a Notice to File Missing Parts of Application is respectfully requested.

[X] A check in the amount of \$ 690.00 is enclosed for the fee due.

[ ] Charge \$ \_\_\_\_\_ to Deposit Account No. 02-4800 for the fee due.

[X] The Commissioner is hereby authorized to charge any appropriate fees under 37 C.F.R. §§ 1.16, 1.17 and 1.21 that may be required by this paper, and to credit any overpayment, to Deposit Account No. 02-4800. This paper is submitted in duplicate.


Please address all correspondence concerning the present application to:

Ronald L. Grudziecki, Esq.  
Burns, Doane, Swecker & Mathis, L.L.P.  
P.O. Box 1404  
Alexandria, Virginia 22313-1404.

Respectfully submitted,

BURNS, DOANE, SWECKER & MATHIS, L.L.P.

Date: August 31, 2000

By:   
Scott W. Cummings  
Registration No. 41,567

P.O. Box 1404  
Alexandria, Virginia 22313-1404  
(703) 836-6620

Utility Patent Application

for

COATED MILLING INSERT

by

ÅKE ÖSTLUND, JEANETTE PERSSON and Rickard SUNDSTRÖM

BURNS, DOANE, SWECKER & MATHIS, L.L.P.

Post Office Box 1404  
Alexandria, Virginia 22313-1404  
Telephone: (703) 836-6620

Date: August 31, 2000

## COATED MILLING INSERT

### **BACKGROUND OF THE INVENTION**

#### Field of the Invention:

The present invention relates to a coated cemented carbide cutting tool, such as an indexable insert, for milling. More particularly, to an insert useful for milling at high cutting speeds in low and medium alloyed steels or milling in hardened steels at high cutting speed, preferably at dry and rather stable conditions, but also for milling in cast iron and some of the stainless steels at high cutting speed.

#### Description of Related Art:

In the description of the background of the present invention that follows reference is made to certain structures and methods, however, such references should not necessarily be construed as an admission that these structures and methods qualify as prior art under the applicable statutory provisions. Applicants reserve the right to demonstrate that any of the referenced subject matter does not constitute prior art with regard to the present invention.

It is well known that for cemented carbide cutting tools used in the machining of steels, the cutting edge is worn by different wear mechanisms such as chemical and abrasive wear but the tool edge may also fracture under a heavy intermittent cutting load, resulting in so called edge chipping which is usually initiated by cracks formed perpendicular to the cutting edge. These type of cracks are called comb cracks. Furthermore, different cutting conditions such as cutting speed, depth of cut, cutting feed rate and also external conditions such as dry or wet machining, vibrations of the work piece, or a surface zone from forging or casting on the work piece, or milling in hardened steels etc., require a plurality of different properties of the cutting edge.

For instance, when milling in a medium alloyed steel where the surface of the work piece material is covered by a so called surface skin-containing areas with high hardness which result

from casting or forging, a coated cemented carbide insert must be used including a substrate of a tough cemented carbide grade having a wear resistant refractory surface coating. When applying a coated carbide cutting insert in milling of a workpiece of a low alloyed steel or a austenitic stainless steel at high cutting speeds, adhesive forces between the chips of the workpiece and the cutting edge will occur causing chipping along the cutting edge. In addition, when milling in ordinary low or medium alloyed steels at very high cutting speeds, the thermal energy developed in the cutting zone is considerable and the entire tool edge may plastically deform independent of the type of coating used. The meaning of high cutting speed is dependent of the properties of the work piece material and other factors related to the cutting operation. High cutting speed is the upper speed range that normally could be found at work shops. Furthermore when milling in hardened steels, hardened to at least 300 Brinell but often above 400-500 Brinell, the mechanical loads encountered normally reduces the tool life by fracture of the tool. When milling in hardened steels at high cutting speed, high mechanical load is encountered in combination with high temperature at the cutting zone, which normally reduces the tool life rather drastically.

Commercial cemented carbide tools for milling in steel, stainless steel or cast iron, at high cutting speeds are usually optimized with respect to one or two of the wear types observed.

US 5,912,051 discloses a coated cutting insert particularly useful for dry milling of grey cast iron. US 5,863,640 discloses a coated turning insert particularly useful for intermittent turning in low alloyed steel.

In US 6,062,776 a coated cemented carbide cutting tool particularly designed for the wet and dry milling of workpieces of low and medium alloyed steels or stainless steels, with or without abrasive surface zones, in machining operations requiring a high degree of toughness of the carbide cutting edge is described. The external cutting conditions are characterized by complex shapes of the workpiece, vibrations, chip hammering, recutting of the chips etc.

In WO 97/20081 a coated cemented carbide cutting tool particularly designed for the wet and dry milling of low and medium alloyed steels is described.

## SUMMARY OF THE INVENTION

It has now surprisingly been found that by combining many different features a cutting tool can be obtained with excellent cutting performance in low and medium alloyed steels at high cutting speed, as well as milling in hardened steels at high cutting speed, in work piece materials with or without abrasive surface zones preferably under stable and dry conditions. It has also been found that this specific cutting tool also works in cast iron and stainless steel at high cutting speed. The cutting tool according to the invention shows improved properties with respect to the different wear types prevailing at these cutting conditions as earlier mentioned.

According to a first aspect, the present invention provides a cutting tool for milling low and medium alloyed steels with or without abrasive surfaces during dry or wet conditions at high cutting speed, and milling hardened steels at high cutting speed, comprising:

a cemented carbide body comprising WC, 7.1-7.9 wt-% Co and 0.2-1.8 wt-% cubic carbides of Ta, Ti and Nb, with Ti present on a level corresponding to a technical impurity, and a highly W-alloyed binder phase with a CW-ratio of 0.85-0.96: and

a coating comprising:

- a first innermost layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , preferably  $z<0.5$ , with a thickness of 0.1-1.5  $\mu\text{m}$ , and with equiaxed grains with a size  $<0.5\mu\text{m}$ ,
- a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , with  $z=0$ ,  $x>0.3$  and  $y>0.3$ , with a thickness of 1-6  $\mu\text{m}$ , and with columnar grains with a diameter of about  $<5\mu\text{m}$ , and
- a layer of a smooth,  $\kappa\text{-Al}_2\text{O}_3$  with a grain size of 0.5-2  $\mu\text{m}$  and with a thickness of 0.5-5  $\mu\text{m}$ .

According to a further aspect, the present invention provides a method of making a cutting tool comprising a WC-Co-based cemented carbide body with a highly W-alloyed binder phase having a CW-ratio of 0.85-0.96, and a coating, the method comprising:

- applying with a CVD technique, a first (innermost) layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ ,  $z<0.5$ , with a thickness of 0.1-1.5  $\mu\text{m}$ , with equiaxed grains with size  $<0.5 \mu\text{m}$ ;
- applying with a MTCVD-technique, using acetonitrile as the carbon and nitrogen source for forming the layer at a temperature range of 850-900°C, a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ ,  $z=0$  and  $x>0.3$  and  $y>0.3$ , with a thickness of 1-6  $\mu\text{m}$  with columnar grains with a diameter of about  $<5 \mu\text{m}$ ; and
- applying a layer of a smooth  $\kappa\text{-Al}_2\text{O}_3$  with a thickness of 0.5-5  $\mu\text{m}$ .

## DETAILED DESCRIPTION OF THE INVENTION

The cutting tool insert according to the invention includes: a cemented carbide body with a rather high W-alloyed binder phase and with a well balanced chemical composition and grain size of the WC, a columnar  $\text{TiC}_x\text{N}_y\text{O}_z$ -layer, a  $\kappa\text{-Al}_2\text{O}_3$ -layer, a TiN-layer and optionally followed by smoothening the cutting edges by brushing, e.g. - brushing with a SiC-based brush.

According to the present invention a coated cutting tool insert is provided consisting of a cemented carbide body with a composition of 7.1-7.9 wt% Co, preferably 7.3-7.9 wt% Co, most preferably 7.4-7.8 wt% Co; 0.2-1.8 wt% cubic carbides, preferably 0.4-1.8 wt% cubic carbides, most preferably 0.5-1.7 wt% cubic carbides of the metals Ta, Nb and Ti; and balance is made up by WC. The cemented carbide may also contain other carbides from elements from group IVb, Vb or VIb of the periodic table. The content of Ti is preferably on a level corresponding to a technical impurity. The average grain size of the WC is in the range of about 1.5-2.2  $\mu\text{m}$ , preferably about 1.8  $\mu\text{m}$ .



The cobalt binder phase is rather highly alloyed with W. The content of W in the binder phase can be expressed as the CW-ratio =  $M_s / (\text{wt\% Co} \cdot 0.0161)$ , where  $M_s$  is the measured saturation magnetization of the cemented carbide body in kA/m and wt% Co is the weight percentage of Co in the cemented carbide. The CW-value is a function of the W content in the Co binder phase. A high CW-value corresponds to a low W-content in the binder phase.

It has now been found according to the present invention that improved cutting performance is achieved if the cemented carbide body has a CW-ratio of 0.85-0.96, preferably 0.86-0.94, and most preferably 0.86-0.93. The cemented carbide may contain small amounts, < 1 volume %, of  $\eta$ -phase ( $M_6C$ ), without any detrimental effect. From the CW-value it follows that no free graphite is allowed in the cemented carbide body according to the present invention.

The coating comprises:

- a first (innermost) layer of  $TiC_xN_yO_z$  with  $x+y+z=1$ , preferably  $z < 0.5$ , more preferably  $y > x$  and  $z < 0.2$ , most preferably  $y > 0.8$  and  $z = 0$ , with equiaxed grains with size  $< 0.5 \mu m$  and a total thickness  $< 1.5 \mu m$  and preferably  $> 0.1 \mu m$ .

- a layer of  $TiC_xN_yO_z$  with  $x+y+z=1$ , preferably with  $z=0$ ,  $x > 0.3$  and  $y > 0.3$ , most preferably  $x > 0.5$ , with a thickness of  $1-8 \mu m$ , preferably  $2-7 \mu m$ , most preferably  $< 6 \mu m$ , with columnar grains and with an average diameter of  $< 5 \mu m$ , preferably  $0.1-2 \mu m$ .

- a layer of a smooth, fine-grained (grain size about  $0.5-2 \mu m$ )  $Al_2O_3$  consisting essentially of the  $\kappa$ -phase. However, the layer may contain small amounts, 1-3 vol-%, of the  $\theta$ - or the  $\alpha$ -phases as determined by XRD-measurement. The  $Al_2O_3$ -layer has a thickness of  $0.5-5 \mu m$ , preferably  $0.5-2 \mu m$ , and most preferably  $0.5-1.5 \mu m$ . The  $Al_2O_3$  layer can be the outermost layer. However, preferably, this  $Al_2O_3$ -layer is followed by a further layer ( $< 1 \mu m$ , preferably  $0.1-0.5 \mu m$  thick) of  $TiC_xN_yO_z$  with  $x+y+z=1$ , preferably with  $y > x$  and  $z < 0.3$ , more preferably  $y > 0.8$ , most preferably  $y = 1$ . The outermost layer,  $Al_2O_3$  (or  $TiC_xN_yO_z$ ), has a

surface roughness  $R_{\max} \leq 0.4 \mu\text{m}$  over a length of  $10 \mu\text{m}$ . The  $\text{TiC}_x\text{N}_y\text{O}_z$ -layer, if present, is preferably removed along the cutting edge. Alternatively, the  $\text{TiC}_x\text{N}_y\text{O}_z$  layer is removed and the underlying alumina layer is partly or completely removed along the cutting edge.

The present invention also relates to a method of making a coated cutting tool insert consisting of a cemented carbide body with a composition of 7.1-7.9 wt% Co, preferably 7.3-7.9 wt% Co, most preferably 7.4-7.8 wt% Co; 0.2-1.8 wt% cubic carbides, preferably 0.4-1.8 wt% cubic carbides, most preferably 0.5-1.7 wt% cubic carbides of the metals Ta, Nb and Ti; and the balance WC. The cemented carbide may also contain other carbides from elements from group IVb, Vb or VIb of the periodic table. The content of Ti is preferably on a level corresponding to a technical impurity. The average grain size of the WC is in the range of about 1.5-2.5  $\mu\text{m}$ , preferably about 1.8  $\mu\text{m}$ . Onto the cemented carbide body is deposited:

- a first (innermost) layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , preferably  $z < 0.5$ , more preferably  $y > x$  and  $z < 0.2$ , most preferably  $y > 0.8$  and  $z=0$ , with equiaxed grains with size  $< 0.5 \mu\text{m}$  and a total thickness  $< 1.5 \mu\text{m}$ , and preferably  $> 0.1 \mu\text{m}$ , using known CVD-methods.

- a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , preferably with  $z=0$ ,  $x > 0.3$  and  $y > 0.3$ , most preferably  $x > 0.5$ , with a thickness of 1-8  $\mu\text{m}$ , preferably 2-7  $\mu\text{m}$ , most preferably  $< 6 \mu\text{m}$ , with columnar grains and with an average diameter of about  $< 5 \mu\text{m}$ , preferably 0.1-2  $\mu\text{m}$ , using preferably MTCVD-technique (using acetonitrile as the carbon and nitrogen source for forming the layer in the temperature range of 700-900° C). The exact conditions, however, depend to a certain extent on the design of the equipment used.

- a smooth  $\text{Al}_2\text{O}_3$ -layer essentially consisting of  $\kappa\text{-Al}_2\text{O}_3$  is deposited under conditions disclosed in e.g. US 5,674,564. The  $\text{Al}_2\text{O}_3$  layer has a thickness of 0.5-5  $\mu\text{m}$ , preferably 0.5-2  $\mu\text{m}$ , and most preferably 0.5-1.5  $\mu\text{m}$ . Preferably, a further layer ( $< 1 \mu\text{m}$ , preferably 0.1-0.5  $\mu\text{m}$  thick) of  $\text{TiC}_x\text{N}_y\text{O}_z$  is deposited, but the  $\text{Al}_2\text{O}_3$ -layer can be the outermost layer. This outermost

layer,  $\text{Al}_2\text{O}_3$  or  $\text{TiC}_x\text{N}_y\text{O}_z$ , has a surface roughness  $R_{\text{max}} \leq 0.4 \mu\text{m}$  over a length of  $10 \mu\text{m}$ . The smooth coating surface can be obtained by a gentle wet-blasting the coating surface with fine grained (400-150 mesh) alumina powder or by brushing (preferably used when  $\text{TiC}_x\text{N}_y\text{O}_z$  top coating is present) the edges with brushes based on, e.g. - SiC as disclosed e.g. in US 5,861,210. The  $\text{TiC}_x\text{N}_y\text{O}_z$ -layer, if present, is preferably removed along the cutting edge. Alternatively, the  $\text{TiC}_x\text{N}_y\text{O}_z$  layer is removed and the underlying alumina layer is partly or completely removed along the cutting edge.

The present invention will now be further described by reference to the following examples, which are intended to be illustrative rather restrictive.

#### Example 1.

A.) A cemented carbide milling tool in accordance with the invention with the composition 7.6 wt-% Co, 1.22 wt-% TaC, 0.30 wt-% NbC and balance is made up by WC, with a binder phase alloyed with W corresponding to a CW-ratio of 0.87 were coated with a  $0.5 \mu\text{m}$  equiaxed  $\text{TiC}_{0.05}\text{N}_{0.95}$ -layer (with a high nitrogen content corresponding to an estimated C/N-ratio of 0.05) followed by a  $4 \mu\text{m}$  thick  $\text{TiC}_{0.54}\text{N}_{0.46}$ -layer, with columnar grains by using MTCVD-technique (temperature  $885\text{--}850^\circ\text{C}$  and  $\text{CH}_3\text{CN}$  as the carbon/nitrogen source). In subsequent steps during the same coating cycle, a  $1.0 \mu\text{m}$  thick layer of  $\text{Al}_2\text{O}_3$  was deposited using a temperature  $970^\circ\text{C}$  and a concentration of  $\text{H}_2\text{S}$  dopant of 0.4 % as disclosed in US 5,674,564. A thin ( $0.3 \mu\text{m}$ ) layer of TiN was deposited on top according to known CVD-technique. XRD-measurement showed that the  $\text{Al}_2\text{O}_3$ -layer consisted of 100 %  $\kappa$ -phase. The cemented carbide body had a WC grain size in average of  $1.7 \mu\text{m}$ .

B.) A cemented carbide milling tool with the composition 9.1 wt-% Co, 1.25 wt-% TaC, 0.30 wt% NbC and the balance is made up by WC, with a binder phase alloyed with W corres-

ponding to a CW-ratio of 0.90. The cemented carbide body had a WC grain size in average of 1.7  $\mu\text{m}$ , and a similar coating compared to the coating on A, but the thickness of the  $\text{Al}_2\text{O}_3$ -layer was 1.2  $\mu\text{m}$ .

C.) A cemented carbide milling tool with the composition 6.0 wt-% Co, and the balance is made up by WC, with a binder phase alloyed with W corresponding to a CW-ratio of 0.90, and a WC grain size is 1.8  $\mu\text{m}$ . The coating is similar to the coating on A, but the thickness of the  $\text{Al}_2\text{O}_3$ -layer was 4.1  $\mu\text{m}$  and this layer is the outermost layer.

Operation:	Face milling - semi finishing
Work-piece:	Support ring
Material:	SS 2242, hardened to 51 HRC
Cutting speed:	100 m/min
Feed rate/tooth:	0.09 mm/rev.
Depth of cut:	0.3-3.5 mm
Insert-style:	RCKT 1606MO
Cutter-body:	R200-084Q32-16M
Note:	six inserts, dry and stable conditions

Results: Tool-life, (average value after three tests per variant) min:

Grade A: 24

Grade B (conv. art): 12

Grade C (conv. art): 14

Tool-life criteria were fracture on rake face of the inserts, and flank wear.

Example 2.

D. A cemented carbide milling tool in accordance with the invention with the composition 7.2 wt-% Co, 1.24 wt-% TaC, 0.29 wt-% NbC and balance WC, with a binder phase alloyed with W corresponding to a CW-ratio of 0.92 were coated with a 0.5  $\mu\text{m}$  equiaxed  $\text{TiC}_{0.05}\text{N}_{0.95}$ -layer (with a high nitrogen content corresponding to an estimated C/N-ratio of 0.05) followed by a 5  $\mu\text{m}$  thick  $\text{TiC}_{0.54}\text{N}_{0.46}$ -layer, with columnar grains by using MTCVD-technique (temperature 885-850°C and  $\text{CH}_3\text{CN}$  as the carbon/nitrogen source). In subsequent steps during the same coating cycle, a 1.5  $\mu\text{m}$  thick layer of  $\text{Al}_2\text{O}_3$  was deposited using a temperature 970°C and a concentration of  $\text{H}_2\text{S}$  dopant of 0.4 % as disclosed in US 5,674,564. A thin (0.3  $\mu\text{m}$ ) layer of TiN was deposited on top according to known CVD-technique. XRD-measurement showed that the  $\text{Al}_2\text{O}_3$ -layer consisted of 100 %  $\kappa$ -phase. The cemented carbide body had a WC grain size in average of 1.8  $\mu\text{m}$ .

E. A commercial cemented carbide cutting tool with the composition of 8.0 wt-% Co, 0.2 wt-% TiC, 1.8 wt-% TaC, 0.2 wt-% NbC, and balance is made up by WC, and CW-ratio of 0.85. The WC-grain size was 1.7  $\mu\text{m}$ . The insert had a conventional CVD-coating consisting of total 4  $\mu\text{m}$  TiC/TiC,N/TiN.

Inserts from B, D and E were tested in a face milling operation.

Operation:	Face milling
	(4 passages per 200 mm)
Work-piece:	Bar, 300x200 mm
Material:	SS2541, HB=300
Cutting speed:	367 m/min
Feed rate/tooth:	0.15 mm/rev.
Depth of cut:	2 mm

Insert-style: SEKN 1204

Note: 6 inserts, dry and stable condition

Results: Tool-life, milled length m, average of two tests

Grade D: 9.0

Grade B (conv. art): 7.8

Grade E (conv. art): 5.7

Tool-life criteria were flank wear and chipping between comb cracks

### Example 3.

Inserts from B and A were tested in face milling

Operation: Face milling - semi finishing

Work-piece: Axle housing

Material: cast steel low alloyed, HB=280

Cutting speed: 228 m/min

Feed rate/tooth: 0.24 mm/rev.

Depth of cut: 1.3-3.2 mm

Insert-style: LNCX 1806AZ R-11

Note: dry, 10 teeth, unstable tendencies

Results: Tool-life, number of component per edge set

Grade A: 5

Grade B: (conv. art) 1

Tool-life criterion was flank wear and plastic deformation.

#### Example 4.

Inserts from A and C were tested in face milling in a hardened plate with holes.

Operation:	Face milling - roughing	
Work-piece:	Plate, 300x220 mm	
Material:	1.2767, machined surface with holes, 54 HRC	
Cutting speed:	67 m/min	
Feed rate/tooth:	0.27 mm/rev.	
Depth of cut:	1 mm	
Insert-style:	RCKT 1204	
Note:	dry, 6 teeth, instability	
Results:	Tool-life, no of passages, min	
Grade A:	18	13.5
Grade C (conv. art):	8	6

Tool-life criterion was flank wear and plastic deformation

#### Example 5.

F. A cemented carbide milling tool in accordance with the invention with the composition 7.2 wt-% Co, 1.24 wt-% TaC, 0.29 wt-% NbC and balance is made up by WC, with a binder phase alloyed with W corresponding to a CW-ratio of 0.89 were coated with a 0.5  $\mu$ m equiaxed

TiC<sub>0.05</sub>N<sub>0.95</sub>-layer (with a high nitrogen content corresponding to an estimated C/N-ratio of 0.05) followed by a 4  $\mu$ m thick TiC<sub>0.54</sub>N<sub>0.46</sub>-layer, with columnar grains by using MTCVD-technique (temperature 885-850°C and CH<sub>3</sub>CN as the carbon/nitrogen source). In subsequent steps during the same coating cycle, a 1.0  $\mu$ m thick layer of Al<sub>2</sub>O<sub>3</sub> was deposited using a temperature 970°C and a concentration of H<sub>2</sub>S dopant of 0.4 % as disclosed in US 5,674,564. A thin (0.3  $\mu$ m) layer of TiN was deposited on top according to known CVD-technique. XRD-measurement showed that the Al<sub>2</sub>O<sub>3</sub>-layer consisted of 100%  $\kappa$ - phase. The cemented carbide body had a WC grain size in average of 1.75  $\mu$ m.

Inserts from F and B were tested in a face milling operation. A cutter body with a diameter of 160 mm were central positioned relatively a rod with a diameter of 90 mm.

Operation:	Face milling
Work-piece:	SS2541 diameter 90 mm, HB=310
Cutting speed:	372 m/min
Feed rate/tooth:	0.32 mm/rev.
Depth of cut:	2 mm
Insert-style:	R245 12T3E-PL
Note:	dry, one tooth

Results: Tool-life, (average 2 tests) min:

Grade F: 13

Grade B(conv. art): 9.5

Tool-life criterion was chipping due to comb crack formation.



Example 6.

Inserts from A and B were tested in cavity milling with round inserts.

Operation:	Cavity milling including ramping
Work-piece:	Orvar Supreme 41 HRC (AISI Prem.H13), 220x250 mm
Cutting speed:	175 m/min
Feed rate/tooth:	0.20 mm/rev.
Depth of cut:	2 mm
Insert style:	RCKT 1204
Note:	dry, some instability
Results:	Tool-life, (average two tests) min:
Grade A:	60
Grade B(conv. art):	21
Tool-life criterion was chipping due to comb crack formation.	

Example 7.

G. A commercial cemented carbide cutting tool with the composition of 7.0 wt-% Co, 0.1 wt-% TiC, 0.7 wt-% TaC, 0.1 wt-% NbC, and balance is made up by WC and CW-ratio of 0.90. The WC-grain size was 2.6  $\mu\text{m}$ . The insert were coated with a 0.3  $\mu\text{m}$  TiN-layer followed by a 0.8  $\mu\text{m}$  thick  $\text{Al}_2\text{O}_3$ -layer, followed by a 0.5  $\mu\text{m}$  TiN-layer followed by a 4.3  $\mu\text{m}$  TiC,N-layer by using MTCVD-technique and finally followed by a 0.2  $\mu\text{m}$  TiN-layer.

Inserts from A, B and G were tested in cavity milling with round inserts.

Operation: Cavity milling including ramping  
Work-piece: Ni max,7 hardened to 390 HB,220x250 mm  
Cutting speed: 250 m/min  
Feed rate/tooth: 0.27 mm/rev.  
Depth of cut: 2 mm  
Insert-style: RCKT 1204 and RPMT 1204  
Note: dry, some instability

Results: Tool-life, min:

Grade A: 55.4

Grade B(conv. art): 32.0

Grade G(conv. art): 14.9

Tool-life criterion was chipping due to comb crack formation.

While the present invention has been described by reference to the above-mentioned embodiments, certain modifications and variations will be evident to those of ordinary skill in the art. Therefore the present invention is to limited only by the scope and spirit of the appended claims.

We Claim:

1. A cutting tool for milling low and medium alloyed steels with or without abrasive surfaces during dry or wet conditions at high cutting speed, and milling hardened steels at high cutting speed, comprising:

a cemented carbide body comprising WC, 7.1-7.9 wt-% Co and 0.2-1.8 wt-% cubic carbides of Ta, Ti and Nb, with Ti present on a level corresponding to a technical impurity, and a highly W-alloyed binder phase with a CW-ratio of 0.85-0.96: and

a coating comprising:

- a first innermost layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ ,  $z<0.5$ , with a thickness of  $0.1\text{-}1.5\text{ }\mu\text{m}$ , and with equiaxed grains with a size  $<0.5\text{ }\mu\text{m}$ ,
- a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , with  $z=0$ ,  $x>0.3$  and  $y>0.3$ , with a thickness of  $1\text{-}8\text{ }\mu\text{m}$ , and with columnar grains with a diameter of about  $<5\text{ }\mu\text{m}$ , and
- a layer of a smooth,  $\kappa\text{-Al}_2\text{O}_3$  with a grain size of  $0.5\text{-}2\text{ }\mu\text{m}$  and with a thickness of  $0.5\text{-}5\text{ }\mu\text{m}$ .

2. The tool according to claim 1 wherein the cemented carbide body has a composition comprising 7.4-7.8 wt-% Co and 0.4-1.8 wt% carbides of Ta and Nb.

3. The tool according to claim 1 further comprising a CW-ratio of 0.86-0.93.

4. The tool according to claim 1 further comprising an outermost TiN-layer.

5. The tool according to claim 4, wherein the outermost TiN layer has been removed at least along a cutting edge of the tool..

6. A method of making a cutting tool comprising a WC-Co-based cemented carbide body with a highly W-alloyed binder phase having a CW-ratio of 0.85-0.96, and a coating, the method comprising:

- applying with a CVD technique, a first (innermost) layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ ,  $z<0.5$ , with a thickness of  $0.1\text{-}1.5\text{ }\mu\text{m}$ , with equiaxed grains with size  $<0.5\text{ }\mu\text{m}$ ;

- applying with a MTCVD-technique, using acetonitrile as the carbon and nitrogen source for forming the layer at a temperature range of  $850\text{-}900^\circ\text{C}$ , a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ ,  $z=0$  and  $x>0.3$  and  $y>0.3$ , with a thickness of  $1\text{-}8\text{ }\mu\text{m}$  with columnar grains with a diameter of about  $<5\text{ }\mu\text{m}$ ; and

- applying a layer of a smooth  $\kappa\text{-Al}_2\text{O}_3$  with a thickness of  $0.5\text{-}5\text{ }\mu\text{m}$ .

7. The method according to the claim 6 wherein said cemented carbide body has a cobalt content of 7.4-7.8 wt% and 0.4-1.8 wt% cubic carbides of Ta and Nb.

8. The method according to claim 6 wherein the cemented carbide body comprises a CW-ratio of 0.86-0.93.

9. The method according to claim 5 further comprising applying an outermost TiN-layer to the body.

10. The method of claim 9 further comprising removing the outermost TiN layer at least along a cutting edge of the tool.

## ABSTRACT

A coated milling insert particularly useful for milling in low and medium alloyed steels with or without abrasive surface zones during dry or wet conditions at high cutting speed, and milling hardened steels at high cutting speed. The insert is characterized by a WC-Co cemented carbide with a low content of cubic carbides and a highly W-alloyed binder phase and a coating including an innermost layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with columnar grains and a top layer of TiN and an inner layer of  $\kappa\text{-Al}_2\text{O}_3$ .

**COMBINED DECLARATION AND POWER OF ATTORNEY  
FOR UTILITY PATENT APPLICATION**

Attorney's Docket No.  
024444-819

As a below-named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name;

I BELIEVE I AM THE ORIGINAL, FIRST AND SOLE INVENTOR (if only one name is listed below) OR AN ORIGINAL, FIRST AND JOINT INVENTOR (if more than one name is listed below) OF THE SUBJECT MATTER WHICH IS CLAIMED AND FOR WHICH A PATENT IS SOUGHT ON THE INVENTION ENTITLED:

COATED MILLING INSERT

the specification of which

(check one)



is attached hereto;



was filed on \_\_\_\_\_ as

Application No. \_\_\_\_\_

and was amended on \_\_\_\_\_;

(if applicable)

I HAVE REVIEWED AND UNDERSTAND THE CONTENTS OF THE ABOVE-IDENTIFIED SPECIFICATION, INCLUDING THE CLAIMS, AS AMENDED BY ANY AMENDMENT REFERRED TO ABOVE;

I ACKNOWLEDGE THE DUTY TO DISCLOSE TO THE OFFICE ALL INFORMATION KNOWN TO ME TO BE MATERIAL TO PATENTABILITY AS DEFINED IN TITLE 37, CODE OF FEDERAL REGULATIONS, Sec. 1.56 (as amended effective March 16, 1992);

I do not know and do not believe the said invention was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to said application; that said invention was not in public use or on sale in the United States of America more than one year prior to said application; that said invention has not been patented or made the subject of an inventor's certificate issued before the date of said application in any country foreign to the United States of America on any application filed by me or my legal representatives or assigns more than twelve months prior to said application;

I hereby claim foreign priority benefits under Title 35, United States Code Sec. 119 and/or Sec. 365 of any foreign application(s) for patent or inventor's certificate as indicated below and have also identified below any foreign application for patent or inventor's certificate on this invention having a filing date before that of the application(s) on which priority is claimed:

# COMBINED DECLARATION AND POWER OF ATTORNEY

Attorney's Docket No.  
024444-819

COUNTRY/INTERNATIONAL

APPLICATION NUMBER

DATE OF FILING  
(day, month, year)

PRIORITY  
CLAIMED

SWEDEN

9903090-0

01-09-99

YES x NO   

YES    NO   

I hereby appoint the following attorneys and agent(s) to prosecute said application and to transact all business in the Patent and Trademark Office connected therewith and to file, prosecute and to transact all business in connection with international applications directed to said invention:

William L. Mathis	17,337	R. Danny Huntington	27,903	Gerald F. Swiss	30,113
Robert S. Swecker	19,885	Eric H. Weisblatt	30,505	Michael J. Ure	33,089
Platon N. Mandros	22,124	James W. Peterson	26,057	Charles F. Wieland III	33,096
Benton S. Duffett, Jr.	22,030	Teresa Stanek Rea	30,427	Bruce T. Wieder	33,815
Norman H. Stepno	22,716	Robert E. Krebs	25,885	Todd R. Walters	34,040
Ronald L. Grudziecki	24,970	William C. Rowland	30,888	Ronni S. Jillions	31,979
Frederick G. Michaud, Jr.	26,003	T. Gene Dillahunty	25,423	Harold R. Brown III	36,341
Alan E. Kopecki	25,813	Patrick C. Keane	32,858	Allen R. Baum	36,086
Regis E. Slutter	26,999	Bruce J. Boggs, Jr.	32,344	Steven M. du Bois	35,023
Samuel C. Miller, III	27,360	William H. Benz	25,952	Brian P. O'Shaughnessy	32,747
Robert G. Mukai	28,531	Peter K. Skiff	31,917	Kenneth B. Leffler	36,075
George A. Hovanec, Jr.	28,223	Richard J. McGrath	29,195	Fred W. Hathaway	32,236
James A. LaBarre	28,632	Matthew L. Schneider	32,814		
E. Joseph Gess	28,510	Michael G. Savage	32,596		



21839

and: Scott W. Cummings, Registration No. 41,567

Address all correspondence to:



21839

Ronald L. Grudziecki  
BURNS, DOANE, SWECKER & MATHIS, L.L.P.  
P.O. Box 1404  
Alexandria, Virginia 22313-1404

Address all telephone calls to: Scott W. Cummings 836-6620.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

FULL NAME OF SOLE OR FIRST INVENTOR		SIGNATURE		DATE	
Åke ÖSTLUND					
RESIDENCE				CITIZENSHIP	
Hägersten, SWEDEN				SWEDEN	
POST OFFICE ADDRESS					
Terrängvägen 96, 129 47 Hägersten, SWEDEN					
FULL NAME OF SECOND JOINT INVENTOR, IF ANY		SIGNATURE		DATE	
Jeanette PERSSON					
RESIDENCE				CITIZENSHIP	
Nacka, SWEDEN				SWEDEN	
POST OFFICE ADDRESS					
Hästhagsvägen 11, 131 13 Nacka, SWEDEN					



**COMBINED DECLARATION AND POWER OF ATTORNEY**Attorney's Docket No.  
024444-819

FULL NAME OF THIRD JOINT INVENTOR, IF ANY	SIGNATURE	DATE
Rickard SUNSTRÖM		
RESIDENCE	CITIZENSHIP	
Johanneshov, SWEDEN	SWEDEN	
POST OFFICE ADDRESS		
Fyrskeppsvagen 85, 1 tr 121 54 Johanneshov		